

MAT PAINT

Guide Formulation

Raw Material	Content [%]
Water	27.13
Hydoxyethylcellulose (HEC)	0.15
NaOH 50%	0.09
Lopon E81	0.20
Disponil A 1080	0.45
Ti-pure R-706 / Kronos 2310	13.74
Durcal 5 / Omycarb 5	21.69
Omycarb Extra CL / Durcal 1	7.00
Mistron 754 G	14.46
OMB 121	13.72
Coapur 830 W / Coapur XS 83	0.15
Associative PU thickener with high shear rate	0.40
Water	0.62
Lopon E81	0.20
Total	100.00

Properties

Solid contents: 64%

Density (20°C): 1.60