

UNIVERSAL PRIMER

Guide Formulation

Raw Material	Content [%]
Water	21.66
Natrosol 250HHBR	0.20
NaOH 50%	0.08
Lopon E81	0.20
Emulsogen LCN 118	0.45
Tiona 595	12.01
Plastorit 00	14.01
Mistron 754 G	10.01
Disperse 15 mins at 4500 RPM / then add under stirring:	
OMB 131	40.05
Coapur XS 83	0.10
Coapur 2025	0.40
Water	0.63
Lopon E81	0.20
Stir 5 minutes	
Total	100.00

Properties

pH value: 11.4
Gloss at 60°: 3.6
Gloss at 85°: 1.6